

AD-A120 259

ROCHESTER UNIV NY DEPT OF CHEMISTRY

F/G 20/12

LASER-STIMULATED ADSPECIES INTERACTION WITH A SEMICONDUCTOR SUR--ETC(U)

SEP 82 W C MURPHY, T F GEORGE

N00014-80-C-0472

UNCLASSIFIED

UROCHESTER/DC/82/TR-24

NL

1 of 1

AD A
120 259



END

DATE

FILED

11-82

DTIC

AD A120259

mtc FILE COPY

(12)

OFFICE OF NAVAL RESEARCH

Contract N00014-80-C-0472

Task No. NR 056-749

TECHNICAL REPORT No. 24

Laser-Stimulated Adsorption Interaction
with a Semiconductor Surface

by

William C. Murphy and Thomas F. George

Prepared for Publication

in

Journal of Physical Chemistry

University of Rochester
Department of Chemistry
Rochester, New York 14627

DTIC
SELECTED
OCT 14 1982
A

September, 1982

Reproduction in whole or in part is permitted for any purpose
of the United States Government.

This document has been approved for public release and sale;
its distribution is unlimited.

82 10 14 010

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER UROCHESTER/DC/82/TR-24	2. GOVT ACCESSION NO. AD-A120259	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Laser-Stimulated Adsorption Interaction with a Semiconductor Surface		5. TYPE OF REPORT & PERIOD COVERED Interim Technical Report
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) William C. Murphy and Thomas F. George		8. CONTRACT OR GRANT NUMBER(s) N00014-80-C-0472
9. PERFORMING ORGANIZATION NAME AND ADDRESS University of Rochester Department of Chemistry Rochester, New York 14627		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS NR 056-749
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research Chemistry Program Code 472 Arlington, Virginia 22217		12. REPORT DATE September 1982
		13. NUMBER OF PAGES 15
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) This document has been approved for public release and sale; its distribution is unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES Prepared for publication in Journal of Physical Chemistry, in press.		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) SURFACE STATES CHARGE DISTRIBUTION SEMICONDUCTOR ENHANCED ADSPECIES-SURFACE INTERACTION SILICON ONE-DIMENSIONAL MODEL LASER EXCITATION QUANTUM MECHANICAL		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) The surface electronic charge distributions of a one-dimensional semiconductor are compared for the ground state and the laser-excited surface states. A charged adsorption interaction potential with these excited surface states is examined for the case of silicon. The use of a laser to enhance desorption or adsorption by this process is discussed.		

DD FORM 1 JAN 73 1473

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

Laser-Stimulated Adsorption
Interaction with a
Semiconductor Surface

William C. Murphy


and

Thomas F. George

Department of Chemistry
University of Rochester
Rochester, New York 14627

Abstract

The surface electronic charge distributions of a one-dimensional semiconductor are compared for the ground state and the laser-excited surface states. A charged adsorption interaction potential with these excited surface states is examined for the case of silicon. The use of a laser to enhance desorption or adsorption by this process is discussed.



1. Introduction

Laser-induced photochemistry with adspecies is a growing area of interest, with much attention being given to desorption processes. For example, Djidjoev and co-workers¹ have reported that the desorption of hydroxyl groups from the surface of silica can be greatly enhanced in the presence of an infrared laser. Chuang² has also presented experimental evidence that the reaction of an adspecies with a silicon surface can be stimulated by laser radiation.

For the theoretical descriptions of these processes, a statistical analysis has been given by Lin et al.,³ while Jedrzejck and his associates⁴ have used a simple one-dimensional model. Both of these theoretical studies, and the experimental works, have relied on the use of the laser to excite the vibrational modes of the system.

On the other hand, photo-induced surface reactions can occur through electronic excitation. Such effects have been demonstrated by synchrotron radiation studies⁵ on metal surfaces. Desorption of an adspecies is produced by a shift in electronic charge in the surface region and the resultant Coulombic repulsion.⁶

For a semiconductor with a surface, the electronic energies consist of various surface states, in addition to the bulk valence and conduction bands.⁷ These surface states, with charge localized in the surface region, can be populated by using a laser to excite electrons from the bulk electronic bands.⁸ As in the case of synchrotron radiation, such surface charge could induce a strong

Coulombic interaction with an adspecies.

In the next section, we calculate the electronic density profile of a model one-dimensional semiconductor, after which the effect of surface state excitation on this curve is examined. The changes in the interaction potential of a charged adspecies with the surface in various excited states is then calculated and compared. Finally, limitations and possible extensions of our model and its application to laser-induced surface processes are discussed.

2. Electronic Density Profile

In our model, we have a one-dimensional linear chain of atoms of length L and with lattice constant a , which is confined along the z -axis to the region $z < a/2$. Such a model has been shown to produce valence, conduction and surface bands.^{7,8} In the ground state, the valence band is completely occupied while the surface and conduction bands are empty.

To obtain the total electron density, $n(z)$, we must sum the individual densities of all occupied states:

$$n(z) = \frac{8L}{(2\pi)^3} \int d^3k |\psi_k(z)|^2 \quad (1)$$

where the wave function, $\psi_k(z)$, with crystal momentum k was previously determined.^{7,8} If we now use cylindrical coordinates, this can be readily reduced to

$$n(z) = \frac{2L}{\pi^2} \int_0^{k_F} dk [E_F - E(k)] |\psi_k(z)|^2 \quad (2)$$

where E_F is the Fermi energy of crystal momentum k_F .

Because of its importance as a semiconductor, we have used parameters^{9,10} typical of silicon to numerically evaluate the density profile, and our results are shown by the solid line in Figure 1. The oscillations of the charge as one goes into the bulk of the crystal and the exponential tail are typical of such density profiles. These results are for the ground electronic state. The effect on this profile of promoting electronic charge by laser action into the surface states is considered below.

3. Charge Density of the Excited System

If the system is now exposed to a laser with an energy of about half the band gap, it is possible to populate surface states of our crystal.⁸ The wave function of these surface states is of the form

$$\psi_{\kappa} = C_s e^{-\kappa(z-\frac{a}{2})} \sin[\frac{g}{2}(z-\frac{a}{2}) + \theta_{\kappa}] \quad (3a)$$

for $z < \frac{a}{2}$ and

$$\psi_{\kappa} = C_s \sin \theta_{\kappa} e^{-q(z-\frac{a}{2})} \quad (3b)$$

for $z > \frac{a}{2}$, with the energy given by

$$E(\kappa) = \frac{1}{2} [(\frac{g}{2})^2 - \kappa^2 \pm (4V^2 - \kappa^2 g^2)^{1/2}] \quad (4)$$

where the normalization constant, C_s , the exponential factor, q , and the phase factor, θ_{κ} , have previously been determined.^{7,8} The parameter κ in the above expressions is the imaginary part of the crystal momentum that occurs in surface states. V , the g component of the Fourier transform of the effective potential where $g = 2\pi/a$ is the reciprocal lattice constant, is assumed to be positive.

Using Equation (1) we find the new charge density to be

$$n(z) = n_0(z) - |\psi_x(z)|^2 + |\psi_\kappa(z)|^2, \quad (5)$$

where $n_0(z)$ refers to the charge density of the unexcited system given by Equation (2) and the transition proceeds from bulk state k to surface state κ . As previously pointed out,⁸ the excitation conserves the crystal momentum. Therefore, bulk states are excited at the band edge with $k = \frac{g}{2}$:

$$\psi_{\frac{g}{2}}(z) = \frac{2}{L^{1/2}} \sin \left[\frac{g}{2} \left(z - \frac{a}{2} \right) + \theta_{\frac{g}{2}} \right]. \quad (6)$$

However, since the charge associated with this state goes as $1/L$, for a very large system we would in effect be taking only an infinitesimal amount of charge from everywhere in the semiconductor to populate the surface state. Consequently, for a large system, the new charge density can be written

$$n(z) = n_0(z) + |\psi_\kappa(z)|^2. \quad (7)$$

Using Equation (3) in Equation (7) along with the results for the ground state, we have obtained the density of the semiconductor with the $\kappa = -.5(2V/g)$ lower branch surface state excited. The results are depicted in Figure 1 by the dashed line. As can be seen by the plot, this excited state produces an electronic charge in the surface region that is twice as great as the bulk average. If the surface states are excited closer to the branch point near the gap center, $\kappa = -2V/g$, the charge concentration in the first few layers of the surface will increase up to about thrice the average density. The interaction of an adspecies with this charged surface will now be examined.

4. Adspecies-Surface Interaction

If there is a charged adspecies above our surface, the classical interaction between this ion and our semiconductor can be written as

$$U(z_I) = - \int n(z) v(r) d\vec{r} \quad (8)$$

with

$$r = [x^2 + y^2 + (z - z_I)^2]^{1/2}, \quad (9)$$

where $v(r)$ is the electron-ion potential of the adspecies at z_I . Let us assume that $v(r)$ is Coulombic in nature with Thomas-Fermi screening:¹¹

$$v(r) = \frac{Ze^{-\lambda r}}{r} \quad (10)$$

where λ is the screening parameter,

$$\lambda^2 = \frac{6\pi\bar{n}}{E_F}, \quad (11)$$

and Z is the charge on the adspecies. A more appropriate screening may well be similar to those developed for finite metals,¹² but such a calculation is beyond the scope of this paper. Since the Thomas-Fermi screening parameter depends on the average electron density, \bar{n} , we would expect this parameter to be less in the surface region. Consequently, the use of a screening parameter based on the bulk density would underestimate the actual interaction.

Bearing this limitation in mind, Equations (8) and (10) can be combined and readily simplified to give the interaction

$$U(z_I) = - \frac{2\pi Z}{\lambda} \int_{-\infty}^{\infty} n(z) e^{-\lambda|z-z_I|} dz. \quad (12)$$

Inserting Equation (7) into this expression, we obtain

$$U(z_I) = - \frac{2\pi Z}{\lambda} \int_{-\infty}^{\infty} n_0(z) e^{-\lambda|z-z_I|} - S U(z_I) dz, \quad (13)$$

where the change in potential induced by the excited surface states is given by

$$S_U(z_I) = \frac{2\pi Z}{\lambda} \int_{-\infty}^{\infty} |\psi_k|^2 e^{-\lambda|z-z_I|} dz. \quad (14)$$

Inserting the expression for the surface wave function, we get

$$S_U(z_I) = \frac{2\pi Z C_S^2}{\lambda} \left\{ \int_{-\infty}^{a/2} \sin^2 \left[\frac{g}{2} \left(z - \frac{a}{2} \right) + \theta_k \right] e^{-2\kappa \left(z - \frac{a}{2} \right) - \lambda|z-z_I|} dz \right. \\ \left. + \sin^2 \theta_k \int_{a/2}^{\infty} e^{-2q \left(z - \frac{a}{2} \right) - \lambda|z-z_I|} dz \right\}. \quad (15)$$

After much algebra, these integrals yield an interaction potential of the form

$$\frac{S_U(z_I)}{z} = e^{-\lambda z_I} A(\kappa) - e^{-2q z_I} B(\kappa), \quad (16)$$

where

$$A(\kappa) = \frac{C_S^2 \pi \sin^2 \theta_k}{\lambda} \left[\frac{1}{(q - \frac{\lambda}{2})} - \frac{1}{2\kappa - \lambda} + \frac{(2\kappa - \lambda) \cos 2\theta_k - g \sin 2\theta_k}{(2\kappa - \lambda)^2 + g^2} \right] e^{\lambda a/2} \quad (17)$$

and

$$B(\kappa) = \frac{C_S^2 4 \pi \sin^2 \theta_k}{(2q)^2 - \lambda^2} e^{q a}. \quad (18)$$

Equation (16) has been evaluated for a number of surface states, and the results are plotted in Figure 2. The curves clearly show that as one moves to larger $|\kappa|$ (energies near the gap center), both the intensity and the range of the surface charge interaction increase, as would be expected from the density calculation. All curves, however, show an appreciable contribution to the potential produced by the surface states with $|\kappa| > 0.1(2V/g)$.

A better comparison of the surface charge interaction among the various surface states is given in Figure 3, where we have plotted the change in potential at $z_I = a$ for all the surface states.

The upper branch states are at a higher energy [positive sign in Equation (4)] than the lower branch states. Therefore, the exponential tail and, subsequently, the interaction is slightly greater.

5. Discussion

Use of a laser to localize electronic charge in the surface region of a semiconductor can produce an appreciable effect on an adspecies-surface interaction. If the adspecies is negatively charged, desorption can be induced; if positively charged, the possibility of adsorption is enhanced. In a more realistic model with both occupied and empty surface states, the laser excitation of holes as well as electrons could be used to selectively enhance adsorption or desorption for the same charged species.

Since the concentration of charge is so great in the surface region, as shown in Figure 1, one would expect the effective interaction length to be greater than that indicated by Figure 2. The exponential decay of our potential is probably an artifact of the assumed Thomas-Fermi screening. An improved interaction potential would necessitate addressing the dielectric screening problem in more detail.¹²

Another consideration is the fact that we did not look at the equilibrium concentration of the surface state - only one surface state was assumed to be populated. On the other hand, several partially occupied surface states may well have as much as or more surface charge than a single occupied surface state.

Of course, the major limitation of our model is its one-dimensionality. The three-dimensional interaction potential may be quite complex depending not only on the distance from the surface

but also on the position of the adspecies with respect to the plane of the surface. Also, many of the features of a crystal cannot be adequately treated in a one-dimensional model.

Nonetheless, our contention that lasers used to control surface charge density can lead to enhanced surface processes has been substantiated. The effects on this process of higher dimensions, phonons, and the dynamics of the adspecies and surface are the subject of continuing research.

Acknowledgments

This work was supported in part by the Office of Naval Research and the Air Force Office of Scientific Research (AFSC), United States Air Force, under Grant AFOSR-82-0046. TFG acknowledges the Camille and Henry Dreyfus Foundation for a Teacher-Scholar Award (1975-1982).


1. M. S. Djidjoev, R. V. Knokhlov, A. V. Kiselev, V. I. Lygin, V. A. Namiot, A. I. Osipov, V. I. Panchenko and B. I. Provotorov, in Tunable Lasers and Applications, edited by A. Mooradian, T. Jaeger and P. Stokseth (Springer, Berlin, 1976).
2. T. J. Chuang, J. Chem. Phys. 74, 1453 (1981).
3. J. Lin, A. C. Beri, M. Hutchinson, W. C. Murphy and T. F. George, Phys. Lett. 79A, 233 (1980).
4. C. Jedrzejek, K. F. Freed, S. Efrima and H. Metiu, Surface Sci. 109, 191 (1981).
5. D. P. Woodruff, M. M. Traum, H. H. Farrell, N. V. Smith, P. D. Johnson, D. A. King, R. L. Benbow and Z. Hurych, Phys. Rev. B 21, 5642 (1980); R. Jaeger, J. Feldhaus, J. Haase, J. Stöhr, Z. Hussain, D. Menzel and D. Norman, Phys. Rev. Lett. 45, 1870 (1980).
6. M. L. Knotek and P. J. Feibelman, Phys. Rev. Lett. 40, 964 (1978).
7. S. Lundqvist, in Surface Science, Vol. 1 (International Atomic Energy Agency, Vienna, 1975), p. 331.
8. W. C. Murphy and T. F. George, Surface Sci. 114, 189 (1982).
9. C. Kittel, Introduction to Solid State Physics, 4th ed. (Wiley, New York, 1971), p. 38, 364.
10. J. Van Laar and J. Scheer, Philips Res. Rept. 17, 101 (1962).
11. See, e.g., C. Kittel, Quantum Theory of Solids (Wiley, New York, 1963), p. 105.
12. D. M. Newns, Phys. Rev. B 1, 3304 (1970); E. Gerlach, in Molecular Processes on Solid Surfaces, E. Dranglis, R. Gretz, and R. Jaffee, eds. (McGraw-Hill, 1969), p. 181.

Figure 1. Electron density distribution at the surface. The solid line represents the ground electronic state, and the dashed line represents the system with the excited surface state $\kappa = -.5 (2V/g)$ in the lower branch.

Figure 2. The magnitude of the surface interaction potential (in millihartrees) at various distances from the surface. The solid line represents the system with excited state $\kappa = -(2V/g)$; the dashed line, $\kappa = -.5(2V/g)$; and the dotted line, $\kappa = -.1(2V/g)$, all in the lower energy branch.

Figure 3. The magnitude of the surface interaction potential (in millihartrees) at a distance $z_I = a$ for the system with various excited surface states. The solid line represents surface states in the lower energy branch; the dashed line, the upper energy branch.

Plot of $n(z)$ vs z/a
of eq 1



1.000 1.000
2.000 2.000





Fig. 2



TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Attn: Code 413 800 North Quincy Street Arlington, Virginia 22217	2	Naval Ocean Systems Center Attn: Mr. Joe McCartney San Diego, California 92152	1
ONR Pasadena Detachment Attn: Dr. R. J. Marcus 1030 East Green Street Pasadena, California 91106	1	Naval Weapons Center Attn: Dr. A. B. Amster, Chemistry Division China Lake, California 93555	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Department of the Navy Washington, D.C. 20360	1	Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Dean William Tolles Naval Postgraduate School Monterey, California 93940	1
Dr. Fred Saalfeld Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1	Scientific Advisor Commandant of the Marine Corps (Code RD-1) Washington, D.C. 20380	1
U.S. Army Research Office Attn: CRD-AA-IP P. O. Box 12211 Research Triangle Park, N.C. 27709	1	Naval Ship Research and Development Center Attn: Dr. G. Bosmajian, Applied Chemistry Division Annapolis, Maryland 21401	1
Mr. Vincent Schaper DTNSRDC Code 2803 Annapolis, Maryland 21402	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1
Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 91232	1	Mr. A. M. Anzalone Administrative Librarian PLASTEC/ARRADCOM Bldg 3401 Dover, New Jersey 07801	1
Dr. David L. Nelson Chemistry Program Office of Naval Research 800 North Quincy Street Arlington, Virginia 22217	1		

TECHNICAL REPORT DISTRIBUTION LIST, 056

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. G. A. Somorjai Department of Chemistry University of California Berkeley, California 94720	1	Dr. W. Kohn Department of Physics University of California (San Diego) La Jolla, California 92037	1
Dr. J. Murday Naval Research Laboratory Surface Chemistry Division (6170) 455 Overlook Avenue, S.W. Washington, D.C. 20375	1	Dr. R. L. Park Director, Center of Materials Research University of Maryland College Park, Maryland 20742	1
Dr. J. B. Hudson Materials Division Rensselaer Polytechnic Institute Troy, New York 12181	1	Dr. W. T. Peria Electrical Engineering Department University of Minnesota Minneapolis, Minnesota 55455	1
Dr. Theodore E. Madey Surface Chemistry Section Department of Commerce National Bureau of Standards Washington, D.C. 20234	1	Dr. Chia-wei Woo Department of Physics Northwestern University Evanston, Illinois 60201	1
Dr. J. M. White Department of Chemistry University of Texas Austin, Texas 78712	1	Dr. Robert M. Hexter Department of Chemistry University of Minnesota Minneapolis, Minnesota 55455	1
Dr. Keith H. Johnson Department of Metallurgy and Materials Science Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	Dr. R. P. Van Duyne Chemistry Department Northwestern University Evanston, Illinois 60201	1
Dr. J. E. Demuth IBM Corporation Thomas J. Watson Research Center P. O. Box 218 Yorktown Heights, New York 10598	1	Dr. S. Sibener Department of Chemistry James Franck Institute 5640 Ellis Avenue Chicago, Illinois 60637	1
Dr. C. P. Flynn Department of Physics University of Illinois Urbana, Illinois 61801	1	Dr. M. G. Lagally Department of Metallurgical and Mining Engineering University of Wisconsin Madison, Wisconsin 53706	1

TECHNICAL REPORT DISTRIBUTION LIST, 056

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. Robert Gomer Department of Chemistry James Franck Institute 5640 Ellis Avenue Chicago, Illinois 60637	1	Dr. K. G. Spears Chemistry Department Northwestern University Evanston, Illinois 60201	1
Dr. R. G. Wallis Department of Physics University of California, Irvine Irvine, California 92664	1	Dr. R. W. Plummer University of Pennsylvania Department of Physics Philadelphia, Pennsylvania 19104	1
Dr. D. Ramaker Chemistry Department George Washington University Washington, D.C. 20052	1	Dr. E. Yeager Department of Chemistry Case Western Reserve University Cleveland, Ohio 44106	1
Dr. P. Hansma Physics Department University of California, Santa Barbara Santa Barbara, California 93106	1	Professor D. Hercules University of Pittsburgh Chemistry Department Pittsburgh, Pennsylvania 15260	1
Dr. J. C. Hemminger Chemistry Department University of California, Irvine Irvine, California 92717	1	Professor N. Winograd The Pennsylvania State University Department of Chemistry University Park, Pennsylvania 16802	1
Dr. Martin Fleischmann Department of Chemistry Southampton University Southampton SO9 5NH Hampshire, England	1	Professor T. F. George The University of Rochester Chemistry Department Rochester, New York 14627	1
Dr. G. Rubloff IBM Thomas J. Watson Research Center P. O. Box 218 Yorktown Heights, New York 10598	1	Professor Dudley R. Herschbach Harvard College Office for Research Contracts 1350 Massachusetts Avenue Cambridge, Massachusetts 02138	1
Dr. J. A. Gardner Department of Physics Oregon State University Corvallis, Oregon 97331	1	Professor Horia Metiu University of California, Santa Barbara Chemistry Department Santa Barbara, California 93106	1
Dr. G. D. Stein Mechanical Engineering Department Northwestern University Evanston, Illinois 60201	1	Professor A. Steckl Rensselaer Polytechnic Institute Department of Electrical and Systems Engineering Integrated Circuits Laboratories Troy, New York 12181	1

TECHNICAL REPORT DISTRIBUTION LIST, 056

	<u>No. Copies</u>	<u>No. Copies</u>
Dr. John T. Yates Department of Chemistry University of Pittsburgh Pittsburgh, Pennsylvania 15260	1	
Professor G. H. Morrison Department of Chemistry Cornell University Ithaca, New York 14853	1	
Captain Lee Myers AFOSR/NC Bolling AFB Washington, D.C. 20332	1	
Dr. David Squire Army Research Office P. O. Box 12211 Research Triangle Park, NC 27709	1	
Professor Ronald Hoffman Department of Chemistry Cornell University Ithaca, New York 14853	1	